

ZINC WHITE

24x12ml

104 +++

PW4

TITANIUM WHITE

8/12/24x12ml

105 +++

PW6,PW4

LEMON YELLOW

12/24x12ml

205 ++

PY3,PW6

YELLOW

8/12/24x12ml

200 ++

PY74,PW6

DEEP YELLOW

202 ++

PY74,PO43,PW6

NAPLES YELLOW RED

224 +++

PBr24

ORANGE

24x12ml

235 ++

PO34,PY3

VERMILION

24x12ml

311 ++

PO34,PR57:1

SCARLET

12/24x12ml

334 ++

PO34,PR57:1

DEEP ROSE

362 +++

PV19,PV23

CARMINE

8/12/24x12ml

318 ++

PR83

VIOLET

536 ++

PV23,PV19

ULTRAMARINE

8/12/24x12ml

504 +++

PB29

COBALT BLUE (ULTRAM.)

24x12ml

512 +++

PB29

PHTHALO BLUE

24x12ml

570 +++

PB15

PRUSSIAN BLUE

24x12ml

508 ++

PB27

SÈVRES BLUE

12/24x12ml

530 +++

PB15,PW6

PHTHALO TURQUOISE BLUE

565 +++

PB15,PG7,PW6

BLUISH GREEN DEEP

637 +++

PB15,PG7

YELLOWISH GREEN

617 ++

PG7,PY74

LIGHT GREEN

601 ++

PG7,PY3

PERMANENT GREEN

8/12/24x12ml

662 ++

PG7,PY3

EMERALD GREEN

24x12ml

615 +++

PG36,PY154,PW6

VIRIDIAN

24x12ml

616 +++

PG7

OLIVE GREEN

24x12ml

620 +++

PG7,PY43,PY128

YELLOW OCHRE

8/12/24x12ml

227 +++

PY42

RAW SIENNA

24x12ml

234 +++

PY42,PR101

RAW UMBER

24x12ml

408 +++

PY42,PR101,PBk11

BURNT SIENNA

12/24x12ml

411 +++

PR101

BURNT UMBER

8/12/24x12ml

409 +++

PR101,PBk11

LIGHT OXIDE RED

339 +++

PR101

COLD GREY

717 +++

PBk9,PW6

WARM GREY

718 +++

PBk9,PR101,PY128,PW6

PAYNE'S GREY

24x12ml

708 +++

PBk11,PB29,PV19

IVORY BLACK

701 +++

PBk9

LAMP BLACK

8/12/24x12ml

702 +++

PBk9,PB29

OPACITY

- transparent
- semi-transparent
- semi-opaque
- opaque

LIGHTFASTNESS

- +++ = at least 100 years lightfast under museum conditions
- ++ = 25 - 100 years lightfast under museum conditions
- + = 10 - 25 years lightfast under museum conditions

The lightfastness has been tested in accordance with ASTM Standards D4303.